



Australian Government

PCT/AU2004/000461


REC'D 06 MAY 2004

WIPO

PCT

Patent Office  
Canberra

I, JULIE BILLINGSLEY, TEAM LEADER EXAMINATION SUPPORT AND SALES hereby certify that annexed is a true copy of the Provisional specification in connection with Application No. 2003901734 for a patent by UNISEARCH LIMITED as filed on 11 April 2003.



WITNESS my hand this  
Twenty-seventh day of April 2004

JULIE BILLINGSLEY  
TEAM LEADER EXAMINATION  
SUPPORT AND SALES

**PRIORITY DOCUMENT**  
SUBMITTED OR TRANSMITTED IN  
COMPLIANCE WITH  
RULE 17.1(a) OR (b)

BEST AVAILABLE COPY

AUSTRALIA  
Patents Act 1990

PROVISIONAL SPECIFICATION

Applicant(s):

UNISEARCH LIMITED

Invention Title:

TRANSPARENT SUPERHYDROPHOBIC COATING

The invention is described in the following statement:

## TRANSPARENT SUPERHYDROPHOBIC COATING

### Technical Field

5

The invention relates to the technology of coatings. In particular, the invention relates to a method of forming superhydrophobic coatings on the surface of a substrate, and superhydrophobic coatings produced by the method.

### Background Art

10

Wettability is an indicator of the affinity of a solid surface for a liquid. The wettability of a surface is dependent on both the physical and chemical heterogeneity of the surface.

15

The contact angle  $\theta$  made by a droplet of liquid on the surface of a solid substrate is used as a quantitative measure of the wettability of the surface. If the liquid spreads completely across the surface and forms a film, the contact angle  $\theta$  is  $0^\circ$ . If there is any degree of beading of the liquid on the surface, the surface is considered to be non-wetting.

20

A surface is usually considered to be hydrophobic if the contact angle of a droplet of water is greater than  $90^\circ$ . Coatings on which water has a contact angle greater than  $90^\circ$  are referred to as hydrophobic coatings. Surfaces with water contact angles greater than  $130^\circ$  are commonly referred to as superhydrophobic. Similarly, coatings on which

25

water has a contact angle greater than  $130^\circ$  are commonly referred to as superhydrophobic coatings.

Hydrophobic surfaces have little or no tendency to absorb water and water forms a discrete droplet on the surface. An example of a hydrophobic surface is a

30

polytetrafluoroethylene (Teflon<sup>TM</sup>) surface. Water contact angles on a polytetrafluoroethylene surface can reach about  $115^\circ$ . This is about the upper limit of hydrophobicity on smooth surfaces. The contact angle of a droplet of water on a surface can be increased, however, by causing the surface to become physically roughened.

35

If the surface is rough or heterogeneous there are usually two contact angles that can be measured. Tilting the substrate until the droplet is about to roll off illustrates this phenomena. The contact angle of the leading edge of the droplet represents the largest

measurable contact angle (called the advancing angle or  $\theta_{adv}$ ). The contact angle of the receding edge or tail of the droplet represents the minimum measurable contact angle (called the receding angle or  $\theta_{rec}$ ). The difference between the advancing and receding contact angles is known as the contact angle hysteresis and defines the degree of dynamic wettability.

The contact angle hysteresis of water indicates the stability of a droplet of water on the surface, the lower the contact angle hysteresis the less stable the droplet is and therefore the easier the water droplet slides off the surface.

Hydrophobic coatings, and in particular superhydrophobic coatings, have many uses. Hydrophobic coatings are used to render surfaces water proof or water resistant. Superhydrophobic coatings have a "self-cleaning" property as dirt, bacteria, spores or other substances which come into contact with the surface cannot readily adhere to the coating and are readily washed off by water. Such coating are used to render surfaces resistant to attachment by water soluble electrolytes, such as acids and alkalies, and by dirt and micro-organisms. Such coatings are also used to render surfaces resistant to icing and fouling.

Methods of forming superhydrophobic coatings, and applying superhydrophobic coatings to surfaces, have been described in the prior art. For example, WO 98/42452 describes a method of preparing superhydrophobic coatings.

However, prior art methods of forming superhydrophobic coatings on the surface of a substrate typically use a significant amount of organic solvents. For example, WO 98/42452 describes a method of forming a superhydrophobic coating on a surface involving applying particles to the surface in the form of a slurry of the particles and an organic solvent such as hexane. The use of such solvents is undesirable as such solvents have adverse environmental effects, and are often toxic and flammable and therefore need to be handled with care. It would therefore be desirable to develop alternative methods of forming superhydrophobic coatings.

Superhydrophobic coatings are generally opaque. This is because the hydrophobicity of such coatings is due to both the chemical hydrophobicity of the surface of the coating and the rough surface structure of the coating. Rough surfaces tend to scatter light which causes the surface of the coating to appear opaque. It would be advantageous to develop a method of forming superhydrophobic coatings on the surface of a substrate

which can be used to produce transparent superhydrophobic coatings. Such coatings could then be applied to surfaces where it is desirable for the coating to be transparent, for example, the surfaces of glass windows.

5 Disclosure of the Invention

The present inventors have now developed a new method of forming superhydrophobic coatings that is an improvement over prior art methods.

- 10 In a first aspect, the present invention provides a method of forming a hydrophobic coating on the surface of a substrate, the method comprising the steps of:
- (a) forming an emulsion comprising particulate material, a decomposable surfactant, water and an organic solvent;
  - (b) applying the emulsion to the surface to form a coating on the surface;
  - (c) exposing the coating to conditions such that all or substantially all of the water and the organic solvent are removed from the coating, and the particles of the  
15 particulate material become bound together and to the surface; and
  - (d) exposing the coating to conditions such that the decomposable surfactant decomposes;
- 20 thereby forming a hydrophobic coating on the surface on which water has a contact angle of at least 130°.

Preferably, the coating formed by the method of the present invention is such that water has a contact angle on the coating of at least 150°, more preferably at least 160°, and most preferably about 165° or more.

25 Without wishing to be bound by theory, it is believed that the decomposition of the decomposable surfactant contributes to the hydrophobicity of the coatings formed by the method of the present invention through the decomposition of the decomposable surfactant producing volatile components, which are emitted from the coating giving the  
30 coatings formed by the method of the present invention a porous surface structure that contributes to the hydrophobicity of the coating.

The method of the invention can be used to prepare thin coatings on a surface. For example, the method can be used to prepare hydrophobic coatings having a thickness of  
35 less than 100 nm. The inventors have surprisingly found that in some embodiments of the present invention, the coatings formed by the method of the present invention, particularly thin coatings having a thickness of less than 100 nm, are transparent to

visible light. Without wishing to be bound by theory, it is believed that the decomposition of the decomposable surfactant results in the coatings formed by the method of the present invention having a porous surface structure which contributes to the hydrophobicity of the coating, and which also, in some coatings formed by the method of the invention, gives the coating a transparent appearance.

In a second aspect, the present invention provides a coating formed by the method according to the first aspect of the present invention.

In a third aspect, the present invention provides an object having a surface at least a portion of which is coated with a hydrophobic coating formed by the method according to the first aspect of the present invention.

In a fourth aspect, the present invention provides a transparent hydrophobic coating on which water has a contact angle of at least 130°.

#### Detailed Description of the Invention

In some cases, the particles of the particulate material may have functional groups capable of binding directly to other particles of the particulate material and to the surface thereby binding the particles together and to the surface. However, more typically, the emulsion further comprises a linking agent capable of binding to the particles and to the surface to bind the particles together and to the surface. In such a case, at step (c) of the method of the invention, the linking agent binds to the particles and the surface, binding the particles together and to the surface.

In some embodiments, the linking agent is a polymer or mixture of polymers capable of binding to two or more of the particles thereby linking the particles by a polymer strand, and capable of binding to the surface and one or more of the particles thereby linking the surface and the one or more particles by a polymer strand. Such a linking agent links the particles by polymer strands covalently bound to the particles, and links the surface and the particles by polymer strands covalently bound to the surface and one or more particles. When the particles of the particulate material have hydroxyl groups on the surface of the particles, suitable polymers include siloxane polymers such as hydroxy terminated polydimethylsiloxane (PDMS), hydroxy terminated polydiphenylsiloxane, hydroxy terminated polyphenylmethylsiloxane, methylhydrosiloxane (and copolymers with dimethylsiloxane), vinylmethoxy siloxane homopolymer, polytrifluoropropylmethylsiloxane (silanol terminated), vinylmethylsiloxane,

dimethylsiloxane copolymer (silanol terminated), and vinylmethylsiloxanes. Other polymers which may be used include modified polystyrene, polyethylenes or fluorinated polymers. Suitable polymers also include triethoxysilyl modified poly-1,2-butadiene and polyethylene-co-trialkoxysilane.

5

In other embodiments, the linking agent is a monomer or mixture of monomers capable of forming a polymer strand linking two or more particles of the particulate material, and capable of forming a polymer strand linking the surface and one or more particles of the particulate material. Such a linking agent links the particles by polymer strands covalently bound to the particles, and links the surface and the particles by polymer strands covalently bound to the surface and one or more particles. Such linking agents may for example, be selected from methyltrimethoxysilane, vinyltrimethylsilane, methyltris(methylethylketoximino)silane, methyltriacetoxysilane, ethyltriacetoxysilane and vinyltriacetoxysilane.

15

When the particles are linked together and to the surface by polymer strands, the method may include a further step during or after step (c) or (d) of exposing the coating to conditions such that the polymer strands linking the particles together or to the surface are further cross-linked as described in the co-pending application filed on the same date titled "Durable Hydrophobic Coatings".

20

The particulate material may consist of particles having substantially equal diameters, or alternatively having a spectrum of diameters. Preferably, at least some of the particles have diameters within the range of from 1 nm to 500  $\mu$ m. More preferably, all or substantially all of the particles have diameters in the range of from 1 nm to 500  $\mu$ m, more preferably in the range of from 1 nm to 100  $\mu$ m, more preferably in the range of from 1 nm to 1  $\mu$ m, still more preferably in the range of from 1 nm to 100 nm, and even more preferably in the range of from 5 nm to 50 nm. In some preferred embodiments, the particulate material consists of particles having an average particle size (diameter) in the range of from 1 nm to 500  $\mu$ m. In some embodiments, the average particle size is in the range from 5 nm to 50 nm. In yet a further embodiment, the average particle size is in the range from 5 nm to 20 nm. In yet a further embodiment, the average particle size is about 15 nm.

25

In a preferred embodiment, the particulate material is silica particles, preferably having an average particle diameter of between 20 nm and 100 nm. Silica is relatively cheap and is readily available as a commercial powdered product known as Aerosil<sup>TM</sup> flamed

30

35

- silica. Although silica and silica-based particulate materials are preferred, other particulate material which has an appropriate particle size could be used. Examples of other such particulate materials include metal particles, glass particles and particles of metal oxides such as titanium oxide, aluminium oxide, zirconium oxide and zinc oxide.
- 5 A mixture of two or more types of particulate materials can be used, eg a mixture of silica particles and particles of a metal oxide.

- In some embodiments of the present invention, the particles of the particulate material are modified by contact with a surface modifier capable of reacting with the particles to enhance the chemical hydrophobicity of the particles, and thus the coating formed by the method of the present invention. Typically, the chemical hydrophobicity is enhanced by the surface modifier reacting with a hydrophilic group on the surface of the particles to remove the hydrophilic group or to convert the hydrophilic group to a hydrophobic group. The surface modifier may also react with the surface of the particles to form functional groups on the surface of the particles to facilitate the binding of the particles to a linking agent in step (c) of the method of the present invention.
- 10  
15

- The particulate material may be contacted with the surface modifier prior to the formation of the emulsion at step (a) of the method. Alternatively, the surface modifier may be included in the emulsion. Accordingly, in some embodiments of the present invention, the emulsion further comprises a surface modifier capable of reacting with at least some of the particles of the particulate material to enhance the chemical hydrophobicity of the particles.
- 20

- 25 The surface modifier may for example be a compound containing one or more condensation cure groups and one or more hydrophobic groups. The one or more condensation cure groups may include one or more of the following groups: acetoxymethoxy, oxime, alkoxy or amine. Such surface modifiers include compounds of the formula  $\text{SiR}(\text{OAc})_3$ , where R is a hydrophobic group such as an alkyl group (e.g. methyl or ethyl), vinyl or trifluoropropyl and Ac is an acetyl group.
- 30

- The same compound may act as both a linking agent and a surface modifier, or alternatively different compounds may be used as the linking agent and the surface modifier.
- 35

The decomposable surfactant may be any surfactant capable of forming an emulsion of



the particulate material, the organic solvent and water and which decomposes in step (d) of the method of invention. Preferably the decomposable surfactant decomposes leaving no residue or only hydrophobic residues in the coating. The decomposable surfactant acts as an emulsifier so that the particulate material, water and organic solvent form an emulsion.

Typically, the decomposable surfactant is polyether modified polydimethylsiloxane or polyethoxylate modified polydimethylsiloxane. These surfactants decompose at about 400°C leaving behind a chemically hydrophobic siloxane residue. That is, the polyether or the polyethoxylate portion of the surfactant decomposes leaving only the hydrophobic siloxane portion. Other decomposable surfactants which may be used include pyridinium, 1-[2-(octadecyloxy)-2-oxoethyl]-chloride (9CI) [CAS 4987-84-2].

The organic solvent is typically a non-polar organic solvent such as toluene, ethyl acetate or xylene. Other suitable organic solvents include, for example, hexane or diethylether.

The emulsion comprising the particulate material, the decomposable surfactant, water and the organic solvent, and optionally, a linking agent and/or a surface modifier, may be formed by thoroughly mixing those components, for example in a ultrasonic bath.

The emulsion may be applied to the surface of the substrate by any known technique of applying an emulsion to a surface. Such techniques include dip coating, spin coating and spray coating. Alternatively, brush or roll application to the surface could be used for some emulsions. For preparing transparent coatings, spin coating is preferred as spin coating can be used to prepare uniform thin coatings on a surface. The emulsion may be applied to the surface to form thick coatings or thin films on the surface.

Step (c) of the method of the invention involves exposing the coating to conditions under which all or substantially all of the water and the organic solvent are removed from the coating and the particles of the particulate material become bound together and to the surface. The conditions will vary depending on the particulate material, the organic solvent and the linking agent, if any, used.

In some embodiments of the invention, the particles of the particulate material become bound together and to the surface at ambient temperatures (for example at about 15 to 25°C). In such a case, step (c) may involve exposing the coating to ambient

temperatures for a time sufficient for all or substantially all of the water and the organic solvent to evaporate from the coating, and for the particles of the particulate material to become bound together and to the surface.

- 5 When a monomer such as methyltriacetoxysilane is used as a linking agent, step (c) typically involves heating the coating to a temperature and for a time effective to evaporate all or substantially all of the water and the organic solvent from the coating and to cause the linking agent to bind the particles of the particulate material together and to the surface.

10

Step (c) may involve exposing the coating to one set of conditions to remove all or substantially all of the water and the organic solvent from the coating, and exposing the coating to a different set of conditions to cause the particles of the particulate material to become bound together and to the surface.

15

Step (d) of the method of the invention involves exposing the coating to conditions under which the decomposable surfactant decomposes.

- 20 When the decomposable surfactant is a surfactant such as polyether modified polydimethylsiloxane or polyethoxylate modified polydimethylsiloxane which decomposes at above ambient temperatures, step (d) typically comprises heating the coating to a temperature effective to cause decomposition of the decomposable surfactant.

- 25 In some embodiments of the present invention, the emulsion further comprises a catalyst for catalysing the decomposition of the decomposable surfactant. An example of such a catalyst is photocatalytic titanium dioxide. Photocatalytic titanium dioxide is typically included in the emulsion in the form of small particles and may therefore form part of the particulate material. In such a case, the titanium dioxide catalyst typically  
30 comprises about 2-10% by weight of the particulate material. If such a catalyst is used, step (d) involves exposing the coating to conditions (e.g. light) effective to cause the catalyst to catalyse the decomposition of the decomposable surfactant.

- In some embodiments of the invention, steps (c) and (d) are carried out simultaneously.  
35 In other embodiments of the invention, step (c) is carried out prior to step (d). Preferably, the particulate material, the decomposable surfactant, the organic solvent, the linking agent, if any, and the catalyst for catalysing the decomposition of the

surfactant, if any, are selected such that steps (c) and (d) can be carried out simultaneously.

5 A particularly preferred particulate material is flame-hydrolysed silica powder, such as that commercially available as Aeorsil™ silica power from Degussa Limited, comprising particles having a primary size in the range of 5 nm to 10 nm. Flame-hydrolysed silica particles contain hydrophilic silanol ( $\equiv\text{Si-OH}$ ) functional groups on the surface of the particles. In preferred embodiments of the method of the invention, these functional groups are converted to hydrophobic siloxane groups ( $\equiv\text{Si-O-Si}\equiv$ ),  
10 either by reaction with a surface modifier or by reaction with a linking agent.

In a preferred embodiment of the present invention, the particulate material comprises flame hydrolysed silica particles, the decomposable surfactant is polyether modified polydimethylsiloxane or polyethoxylate modified polydimethylsiloxane, and the  
15 emulsion includes methyltriacetoxysilane. In this embodiment of the present invention, the methyltriacetoxysilane acts both as a surface modifier to increase the chemical hydrophobicity of the silica particles and also acts as a linking agent. During the method of the invention, the methyltriacetoxysilane forms polymer strands linking the silica particles together and to the surface. In this embodiment of the invention, steps  
20 (c) and (d) can be carried out by heating the coating to about 450°C.

The method of the present invention has an advantage in that by using an emulsion of an organic solvent in water, the method involves the use of less volatile organic compounds than some prior art methods of preparing superhydrophobic coatings. In  
25 addition, the emulsion is easier to handle than a slurry of particulate material in an organic solvent. In addition, the decomposition of the decomposable surfactant enhances the roughness of the surface of the coatings formed by the method of the present invention, contributing to the hydrophobicity of the coating. Further, in some embodiments, the coatings formed by the method of the present application are  
30 transparent.

The hydrophobicity of the coatings formed by the method of the present invention is due to a combination of both the chemical hydrophobicity of the surface of the coating and the physical surface structure of the surface of the coating. Accordingly, during the  
35 method of the present invention, the particles of the particulate material, if not initially chemically hydrophobic, typically become chemically hydrophobic. The particles of the particulate material may become chemically hydrophobic as a result of the particles

binding to other particles, reacting with a linking group, or reacting with a surface modifier. Similarly, it is preferred that if a linking agent is used, the linking agent reacts with the particles, the surface modifier or other molecules of the linking agent to form chemically hydrophobic groups, such as hydrophobic polymer strands, linking the particles together and to the surface.

The method of the present invention can be used to form coatings on the surface of a wide variety of substrates including metals, alloys, glasses, ceramics, composites, fabrics, and other materials.

10

The hydrophobic coatings formed by the method of the present invention have many applications. For example, the hydrophobic coatings can be used to render surfaces of a substrate water resistant or water proof. Such coatings can also be used to reduce icing and fouling of surfaces of a substrate. Such coatings can also be used to render a surface resistant to attachment by water soluble electrolytes, such as acids and alkalines, or other material, such as dirt or microorganisms.

15

Transparent hydrophobic coatings produced by the method of the invention have many practical applications, such as coatings for eye glasses, optical lenses, cover glasses for solar cells, wind shields of automobiles, use on traffic signs or lights, windows, mirrors, tiles etc.

20

The invention will now be described by reference to the following non-limiting examples.

25

#### **Example 1**

A hydrophobic coating was prepared using the following procedure:

- The following components were mixed together:
  - 0.05g of polyethoxylate modified PDMS (hydroxy terminated)
  - 0.017g of methyltriacetoxysilane
  - 1.045g of fumed silica powder (having a primary particle size of 5 to 50 nm)
  - 3.33ml of hexane
  - 0.85ml of water
- The mixture was mixed vigorously and vibrated in an ultrasonic bath for 30 minutes to disperse the particles and form a uniform emulsion. Vibration frequencies of about 40kHz were used.

30

35

- The emulsion was removed from the ultrasonic bath.
- Drops of the emulsion were deposited onto the surface of a glass substrate using spin coating. Dip coating or spray coating could alternatively have been used to deposit the emulsion onto the surface.
- 5 • The coated substrate was placed in oven at a temperature of about 450°C for 30 minutes forming a hydrophobic coating on the surface of the substrate.

10 The contact angle and contact angle hysteresis of water and the transmittance of the coating were then measured. The contact angle and contact angle hysteresis were measured using an automated contact angle instrument goniometer (made by Raméhart, Inc). The transmittance was determined by visible spectral analysis.

15	Contact angle:	165°
	Hysteresis:	10°
	Transmittance:	96%

#### Example 2

A hydrophobic coating was prepared using the following procedure:

- 20 • The following components were mixed together:
  - 0.05g of polyethoxylate modified PDMS (hydroxy terminated)
  - 0.017g of methyltriacetoxysilane
  - 0.067g of fumed silica powder (having a primary particle size of 5 to 50 nm)
  - 0.83ml of hexane
  - 25 3.33ml of water
- The mixture was mixed vigorously and vibrated in an ultrasonic bath for 30 minutes to disperse the particles and form a uniform emulsion. Vibration frequencies of about 40kHz were used.
- The emulsion was removed from the ultrasonic bath.
- 30 • Drops of the emulsion were deposited onto the surface of a glass substrate using spin coating. Dip coating or spray coating could alternatively have been used to deposit the emulsion onto the surface of the glass substrate.
- The coated substrate was placed in oven at a temperature of about 450°C for 30 minutes forming a coating on the surface of the glass substrate.

35

The contact angle and contact angle hysteresis of water and the transmittance of the coating were then measured. The contact angle and contact angle hysteresis were

measured using an automated contact angle instrument goniometer (made by Raméhart, Inc). The transmittance was determined by visible spectral analysis.

	Contact angle:	142°
5	Hysteresis:	50°
	Transmittance:	100%

10 In the claims which follow and in the preceding description of the invention, except where the context requires otherwise due to express language or necessary implication, the word "comprising" and grammatical variations thereof is used in an inclusive sense, i.e. the features specified may be associated with further features in various embodiments of the invention.

CLAIMS:

- 1      A method of forming a hydrophobic coating on the surface of a substrate, the  
method comprising the steps of:
  - 5      (a)      forming an emulsion comprising particulate material, a decomposable  
surfactant, water and an organic solvent;
  - (b)      applying the emulsion to the surface to form a coating on the surface;
  - (c)      exposing the coating to conditions such that all or substantially all of  
10      the water and the organic solvent are removed from the coating, and  
the particles of the particulate material become bound together and to  
the surface; and
  - (d)      exposing the coating to conditions such that the surfactant  
decomposes;thereby forming a hydrophobic coating on the surface on which the water has a  
15      contact angle of at least 130°.
2.      A method accordingly to claim 1 wherein the emulsion further comprises a  
linking agent capable of binding to the particles of the particulate material and  
to the surface to bind the particles together and to the surface.  
20
3.      A method according to claim 2 wherein the linking agent is a polymer or  
mixture of polymers capable of binding to two or more of the particles thereby  
linking the particles by a polymer strand, and capable of binding to the surface  
and one or more of the particles thereby linking the surface and the one or  
25      more particles by a polymer strand.
4.      A method according to claim 2 wherein the linking agent is a monomer or  
mixture of monomers capable of forming a polymer strand linking two or more  
of the particles, and capable of forming a polymer strand linking the surface  
30      and one or more of the particles.
5.      A method according any one of claims 1 to 4 wherein the emulsion further  
comprises a surface modifier capable of reacting with at least some of the  
particles of the particulate material to increase the hydrophobicity of the  
35      particles.
6.      A method according to claim 5 wherein the surface modifier is a compound

containing one or more condensation cure groups and one or more hydrophobic groups.

- 5 7. A method according to claim 6 wherein the surface modifier is a compound of the formula  $\text{SiR}(\text{OAc})_3$ , where R is an alkyl group, vinyl or trifluoropropyl, and Ac is an acetyl group.
8. A method according to any one of claims 1 to 7 wherein the particulate material comprises silica particles.
- 10 9. A method according to claim 8 wherein the silica particles are flame hydrolysed silica particles.
- 15 10. A method accordingly to any one of claims 1 to 7 wherein the particulate material comprises metal particles, glass particles or particles of a metal oxide.
11. A method according to claim 10 wherein the metal oxide is titanium oxide, aluminium oxide, aluminium oxide, zirconium oxide or zinc oxide.
- 20 12. A method according to any one of claims 1 to 11 wherein the particles of the particulate material have an average particle size of from 1 nm to 500  $\mu\text{m}$  metres.
- 25 13. A method according to claim 12 wherein the average particle size of the particles of the particulate material is in the range of from 1 nm to 100  $\mu\text{m}$ .
14. A method according to claim 12 wherein the average particle size of the particles of the particulate material is in the range of from 1 nm to 50 nm.
- 30 15. A method according to any one of claims 1 to 14 wherein the decomposable surfactant is polyether modified polydimethylsiloxane, polyethoxylate modified polydimethylsiloxane or pyridinium.
- 35 16. A method according to any one of claims 1 to 15 wherein the organic solvent is selected from toluene, ethylacetate, xylene, hexane or diethylether.
17. A method according to any one of claims 1 to 16 wherein step (c) involves



heating the coating to a temperature and for a time effective to remove all or substantially all of the water and organic solvent from the coating and for the particles of the particulate material to become bound together and to the surface.

5

18. A method according to any one of claims 1 to 14 wherein step (d) involves heating the coating to a temperature and for a time effective to cause decomposition of the decomposable surfactant.

10

19. A method according to any one of claims 1 to 18 wherein steps (c) and (d) are carried out simultaneously.

20. A method according to any one of claims 1 to 18 wherein step (c) is carried out prior to step (d).

15

21. A coating formed by the method according to any one of claims 1 to 20.

22. An object having a surface at least a portion of which is coated with a hydrophobic coating formed by the method according to any one of claims 1 to 20.

20

23. A transparent hydrophobic coating on which water has a contact angle of at least 130°.

25

Dated this 11<sup>th</sup> day of April 2003

UNISEARCH LIMITED

By their Patent Attorneys

30

GRIFFITH HACK

This Page is inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ BLACK BORDERS
- ☒ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☐ BLURED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☒ COLORED OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REPERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY.
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images  
problems checked, please do not report the  
problems to the IFW Image Problem Mailbox**